

Technisches Datenblatt / Technical Data Sheet

Naturgraphit / Natural Graphite
Sorte / Grade

Bläh-Graphit 95 50 350 / Expandable Graphite 95 50 350

Spezifikationen / Specified properties

min. 95% C

min. 70% >300 micron (50 mesh)

Blähfaktor min. 350 ml/g
expansion rate min. 350 ml/g

Authorized signature



Christoph Frey

Version 1.0 issued 22.11.2016